

RYSZARD SPRYCHA ET AL.
USSN 09/982,496
REPLY TO THE OFFICE ACTION DATED JANUARY 4, 2006
AMENDMENT OF APRIL 4, 2006

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (Currently Amended) A non-aqueous ~~lamination~~ ink formulation or dispersion comprising: (a) a hot-melt polyamide resin; (b) a ~~non-fluorescent~~ pigment; (c) an organic solvent; and (d) a viscosity stabilizing, resolubility promoting, water soluble compound selected from the group consisting of base, aminoalcohol, acid and aminoacid.

2. (Canceled)

3. (Currently Amended) The ink formulation or dispersion of claim 1, wherein the ~~non-fluorescent~~ pigment is selected from the group consisting of monoazo yellow, monoarylide yellow, diarylide yellow, naphtol red, rubine red, lithol rubine, phtalocyanine blue and carbon black.

4. (Original) The ink formulation or dispersion of claim 1, wherein the organic solvent is selected from the group consisting of ethanol, n-propanol, iso-propanol, butanol and propyl acetate.

RYSZARD SPRYCHA ET AL.

USSN 09/982,496

REPLY TO THE OFFICE ACTION DATED JANUARY 4, 2006

AMENDMENT OF APRIL 4, 2006

5. (Original) The ink formulation or dispersion of claim 1, wherein the amount of the water soluble compound is about 0.01 to 5.0% by weight of the total weight of the formulation or dispersion.

6. (Original) The ink formulation or dispersion or claim 1, wherein the amount of the water soluble compound is about 0.1 to 1.0% by weight of the total weight of the formulation or dispersion.

7. (Previously presented) The ink formulation or dispersion of claim 1, wherein the base is an inorganic or organic base.

8. (Original) The ink formulation or dispersion of claim 7, wherein the inorganic base is selected from the group consisting of sodium hydroxide, potassium hydroxide and ammonium hydroxide.

9 (Previously Presented) The ink formulation or dispersion of claim 7, wherein the organic base is an amine.

10. (Previously Presented) The ink formulation or dispersion of claim 9, wherein the amine is selected from the group consisting of monoethanolamine, triethanolamine, dimethylethanolamine and diethylenetriamine.

RYSZARD SPRYCHA ET AL.

USSN 09/982,496

REPLY TO THE OFFICE ACTION DATED JANUARY 4, 2006

AMENDMENT OF APRIL 4, 2006

11. (Original) The ink formulation or dispersion of claim 1, wherein the aminoalcohol is selected from the group consisting of aminopropanol, aminoethylpropanediol, aminobutanol, diethylaminoethanol and dimethylaminopropanol.

12. (Original) The ink formulation or dispersion of claim 1, wherein the acid is organic or inorganic acid.

13. (Original) The ink formulation or dispersion of claim 12, wherein the inorganic acid is selected from the group consisting of hydrochloric acid, nitric acid and sulfuric acid.

14. (Original) The ink formulation or dispersion of claim 12, wherein the organic acid is selected from the group consisting of acetic acid, citric acid, and paraaminobenzoic acid.

15. (Currently Amended) A method of increasing the stability and resolubility of a non-aqueous inks formulations or dispersions containing (a) a hot-melt polyamide resin; (b) a pigment; and (c) an organic solvent comprising adding to said formulation or dispersion a water-soluble compound selected from the group consisting of base, aminoalcohol, acid and aminoacid.

16. (Canceled)

RYSZARD SPRYCHA ET AL.
USSN 09/982,496
REPLY TO THE OFFICE ACTION DATED JANUARY 4, 2006
AMENDMENT OF APRIL 4, 2006

17. (Original) The method of claim 15, wherein the pigment is selected from the group consisting of monoazo yellow, monoarylide yellow, diarylide yellow, naphthol red, rubine red, lithol rubine, phthalocyanine blue and carbon black.

18. (Original) The method of claim 15, wherein the organic solvent is selected from the group consisting of n-propanol, iso-propanol, butanol, ethanol and propyl acetate.

19. (Original) The method of claim 15, wherein the amount of the water soluble compound is about 0.01 to 5.0% by weight of the total weight of the formulation or dispersion.

20. (Original) The method of claim 15, wherein the amount of the water soluble compound is about 0.1 to 1.0% by weight of the total weight of the formulation or dispersion.

21. (Original) The method of claim 15, wherein the base is inorganic or organic base.

22. (Original) The method of claim 21, wherein the inorganic base is selected from the group consisting of sodium hydroxide, potassium hydroxide and ammonium hydroxide.

23. (Original) The method of claim 21, wherein the organic base is amine or aminoalcohol.

RYSZARD SPRYCHA ET AL.
USSN 09/982,496
REPLY TO THE OFFICE ACTION DATED JANUARY 4, 2006
AMENDMENT OF APRIL 4, 2006

24. (Original) The method of claim 23, wherein the amine is selected from the group consisting of monoethanolamine, triethanolamine, dimethylethanolamine and diethylenetriamine.

25. (Original) The method of claim 15, wherein the aminoalcohol is selected from the group consisting of aminopropanol, aminoethylpropanediol, aminobutanol, diethylaminoethanol and dimethylaminopropanol.

26. (Original) The method of claim 15, wherein the acid is organic or inorganic acid.

27. (Original) The method of claim 26, wherein the inorganic acid is selected from the group consisting of hydrochloric acid, nitric acid and sulfuric acid.

28. (Original) The method of claim 26, wherein the organic acid is selected from the group consisting of acetic acid, citric acid and paraaminobenzoic acid.

29. (Currently Amended) An improved non-aqueous ~~lamination~~ ink formulation or dispersion comprising: (a) a hot-melt polyamide resin; (b) a ~~non-fluorescent~~ pigment; (c) an organic solvent; wherein the improvement is (d) a viscosity stabilizing, resolubility promoting water soluble compound selected from the group consisting of base, aminoalcohol, acid and aminoacid.

RYSZARD SPRYCHA ET AL.
USSN 09/982,496
REPLY TO THE OFFICE ACTION DATED JANUARY 4, 2006
AMENDMENT OF APRIL 4, 2006

30. (Currently Amended) A non-aqueous ink formulation or dispersion comprising:
(a) a **hot-melt** polyamide resin; (b) a pigment selected from the group consisting of monoazo yellow, monoarylide yellow, diarylide yellow, naphtol red, rubine red, lithol rubine, phtalocyanine blue and carbon black; (c) an organic solvent selected from the group consisting of ethanol, n-propanol, iso-propanol, butanol and propyl acetate; and (d) a viscosity stabilizing, resolubility promoting, water-soluble compound selected from the group consisting of sodium hydroxide, potassium hydroxide, ammonium hydroxide, monoethanolamine, triethanolamine, dimethylethanolamine, diethylenetriamine, aminopropanol, aminoethylpropanediol, aminobutanol, diethylaminoethanol, dimethylaminopropanol, hydrochloric acid, nitric acid and sulfuric acid; and wherein water is excluded.